



Sheepwalk, Frenchpark
 Co. Roscommon.
 Telephone:
 (094) 9870700
 Facsimile:
 (094) 9870797
 email:
 ecoflex@eircom.net
 www.ecoflex.ie

SCRIM TEST RESULTS

***Tests carried out on different areas of Ecoflex Microsurfacing
 to determine Sideways Force Co-Efficient (SFC)
 and Average Scrim Co-Efficient (SC)***

<u>MATERIAL</u>	<u>DATE LAID</u>	<u>DATE SURVEYED</u>	<u>AVERAGE SFC</u>	<u>AVERAGE SC</u>
Ecoflex Microsurfacing	2011	Jan 2012	0.83	0.55
Ecoflex Microsurfacing	2011	Jan 2012	0.88	0.59
Ecoflex Microsurfacing	2011	Jan 2012	0.7	0.46
Ecoflex Microsurfacing	2011	Jan 2012	0.76	0.51
Ecoflex Microsurfacing	2011	Jan 2012	0.9	0.59
Ecoflex Microsurfacing	2011	Jan 2012	0.89	0.59
Ecoflex Microsurfacing	2011	Jan 2012	0.63	0.42