

MICROSURFACING SPECIFICATION

| SPECIFICATION | | |
|----------------------|--|---|
| AGGREGATE | Sieve Size 8mm 6.3mm 5mm 4mm 2.8mm 2 mm 1 mm 500micron | % Passing 100% 95 - 100% 75 - 100% 60 -85% 40 - 65% 22 - 45% 15 - 30% 10 - 20% |
| FILLER | Ordinary Portland Cement | |
| BINDER | Polymer Modified Emulsion Binder Content: 8-10% by weight. Latexfalt Spectrafalt Emulsion can be used to enhance colour if pigment is required. | |
| WATER | Regular Drinking Water | |
| PIGMENT | Dye can be added if required | |
| DEPTH | Typical depth of 8mm per layer (Depending on Individual Site Conditons) Can go to a depth of 80mm if required for rut filling. | |
| CURE TIME | 15 minutes + | |